



EPOXY NOVOLAC GROUT

Highly Chemical Resistant Epoxy Grout

PRODUCT DESCRIPTION

Five Star® Epoxy Novolac Grout is a three component, highly chemical resistant, 100% solids grout designed for industrial applications in aggressive chemical environments where exposure to concentrated acids, alkalis, corrosives or solvents can occur. Five Star® Epoxy Novolac Grout has excellent flowability, is highly chemical resistant, and exhibits positive expansion when tested in accordance with ASTM C 827.

ADVANTAGES

- High chemical resistance
- 95% Effective Bearing Area (EBA)
- Exhibits positive expansion per ASTM C 827
- Excellent impact and wear resistance
- Expansive, nonshrink
- Superior bond to concrete or steel

USES

- Grouting for machinery/pump baseplates
- High chemical resistance requirements
- Process equipment
- Secondary containment

PACKAGING AND YIELD

Five Star® Epoxy Novolac Grout is a three component system consisting of premeasured containers of resin and hardener and four polyethylene lined bags of aggregate and is available in a unit yielding approximately 1.75 cubic feet (49.5 liters) of hardened material.

SHELF LIFE

Two years in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)	
Height Change, ASTM C 827 at 90°F (32°C)	Positive Expansion
Effective Bearing Area	95%
Compressive Strength, ASTM C 579 B*	
1 Day	16,000 psi (110 MPa)
7 Days	17,000 psi (117 MPa)
Post cured at 140° F (60° C)	18,000 psi (124 MPa)
Bond Strength, ASTM C 882	
7 Days	2,500 psi (17.3 MPa)
Tensile Strength, ASTM C 307	2,300 psi (15.9 MPa)
Flexural Strength, ASTM C 580	6,000 psi (41.4 MPa)
Coefficient of Expansion, ASTM C 531	16 x 10 ⁻⁶ in/in/°F (29 x 10 ⁻⁶ mm/mm/°C)
Working Time at 70°F (21°C)	20 minutes

Chemical Resistance Chart* at 70°F (21°C)		
Solvents	Organics Acids (Conc.)	Bases / Alkalines (Conc.)
Acetaldehyde	Acetic (1-50%)	Ammonia (1-25%)
Acetone	Acid plating solutions	Ammonium Hydroxide (1-25%)
Acetonitrile	Adipic (1-25%)	Aniline
Acrylonitrile	Azotic (1-50%)	Barium Hydroxide (1-sat.)
Butyl acetate	Battery (1-98%)	Black Pulp Liquor
Cyclohexane	Chromic (1-30%)	Butyl Amine
Ethanol	Chlorohydric (1-37%)	Cadmium Cyanide Plating
Ethyl acetate	Dibasic (1-sat.)	Calcium Hydroxide (1-25%)
Ethyl alcohol	Ethanoic (1-50%)	Chromium Trioxide (1-25%)
Formaldehyde	Ethylic (1-50%)	Copper Cyanide Plating
Isopropyl Alcohol	Engravers (1-50%)	Dimethyl Aniline
Jet Fuel	Hydrochloric (1-37%)	Hydrogen Peroxide (1-30%)
Kerosene	Hydrofluoric (1-40%)	Green Pulp Liquor
Methyl Ethyl Ketone	Mattling (1-98%)	Soap solutions
Methanol	Nitric (1-50%)	Sodium Cyanide (1-15%)
Methyl Alcohol	Oil of vitriol (1-98%)	Sodium Hypochlorite (1-9%)
Rubbing Alcohol	Oleic	Sodium Hydroxide (1-50%)
Wood Alcohol	Phosphoric (1-85%)	Triethanolamine
1,1,1 Trichloroethane	Sulfuric (1-98%)	Triethylamine
Phenol	Vitriol (1-98%)	Potassium Hydroxide (1-sat)

* NOTE: Many factors effect chemical resistance. Application design, service and exposure temperatures, and the type and amount of impurities in the chemical or in the environment are some important considerations. These test results are reported to serve as a guide to the applicability of the Novolac systems.

*Materials tested per ASTM C 579 B. Rate of loading 0.25 inches per minute. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

PLACEMENT GUIDELINES

- SURFACE PREPARATION:** All surfaces to be in contact with Five Star® Epoxy Novolac Grout shall be free of dust, oil, grease, laitance curing compounds, and other contaminants. Concrete must be clean, sound, dry and roughened to ensure a good bond. An SSPC-SP6 commercial finish on all metal surfaces will optimize bond development to steel.
- FORMWORK:** Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be sufficient to allow for a headbox. The clearance for remaining sides shall be 1 to 2 inches (25 - 50 mm). Areas where bond is not desired must be treated with paste wax or polyethylene. Isolation joints may be necessary depending on pour dimensions. Contact the Five Star Products' Engineering and Technical Service Center for further information.
- MIXING:** For optimum performance, all components should be conditioned to between 65°F and 85°F (18°C and 29°C) prior to use. Pour all Component B (hardener) into pail containing Component A (resin). Mix thoroughly by hand with a paddle or with a slow speed drill and paddle mixer to avoid air entrapment. Pour mixed liquids into mortar mixer (stationary barrel with moving blades). While mixing, slowly add Component C (aggregate) and mix only until aggregate is completely wet out. Working time is approximately 20 minutes when temperatures are at 70°F (21°C).
- METHODS OF PLACEMENT:** Five Star® Epoxy Novolac Grout may be poured into place. All grout shall be placed from one side to the other, maintaining contact with the bottom of the baseplate at all times. When possible, use of a headbox is highly recommended (refer to the Five Star® Technical Bulletin "Head Box and Plunger" for guidelines). For clearances less than 1/2 inch (13 mm) or greater than 6 inches (152 mm) call the Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.
- POST-PLACEMENT PROCEDURES:** Final finishing should ensure material is flush with bottom edge of baseplate. Finishing of exposed surfaces is aided by using a solvent wiped trowel just before material becomes unworkable. In-service operation may begin immediately after minimum required grout strength and modulus have been achieved.
- CLEAN UP:** All tools and equipment may be cleaned with a water and strong detergent solution before material hardens. Sand may be used as an abrasive. A suitable solvent is required for clean up of material after hardening.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Design-A-Spec™ installation guidelines or call the Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CONSIDERATIONS

- Flowability and strength gain are adversely affected by lower temperatures.
- For placement temperatures below 55°F (13°C) or above 90°F (32°C), refer to Design-A-Spec™.
- To obtain bond, concrete shall be visibly free of surface moisture.
- When clearances are outside the recommended range or when exceeding maximum placement volumes, contact Five Star Products' Engineering and Technical Service Center.
- Do not add solvents to increase flowability.
- For continuous operating temperatures exceeding 200°F (93°C), contact the Five Star Products' Engineering and Technical Service Center.
- Construction practices dictate concrete foundation should achieve its design strength before grouting.

CAUTION

FOR INDUSTRIAL USE ONLY. Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

SKU / PRODUCT CODE	DESCRIPTION	# UNITS/PALLET	WEIGHT
34975	Five Star® Epoxy Novolac Grout	36 (packaged on 4 pallets)	227.5 lbs. (103.2 Kg)

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Five Star Products, Inc.
Corporate Headquarters
750 Commerce Drive
Fairfield, CT 06825 USA
Tel: +1 203-336-7900 • Fax: +1 203-336-7930
FiveStarProducts.com

Specifications Subject to Change.

For most current version of datasheet, go to FiveStarProducts.com

© 2015 Five Star Products, Inc. | 04-09-2015
American Owned & Operated

